ELI-CAST FR/453 ELECTRICAL INSULATING RESIN

PRODUCT:	Eli-Cast FR/453 is filler extended two part Polyurethane Resin			
COLOUR:	Resin: Hardener: Mixed:	Electro Brown Brownish clear Electro Brown		
VISCOSITY / 25°C:	Resin: Hardener: Mixed:	5 000 – 5 500 mPa.s 200 – 200 mPa.s 2 000 – 2 500 mPa.s		
APPLICATION:	By casting			
MIXING RATIO:	<u>By Weight</u> 100 parts of Re 25 – 26 parts of Ha		<u>By Volume</u> 100 parts of Re 34 – 35 parts of Ha	
SPECIFIC GRAVITY:	Resin: Hardener:	1.65 g/cm ³ 1.20 g/cm ³		
POTLIFE / 25°C:	30 Minutes			
GELTIME / 25°C:	35 – 40 Minutes			
SETTING TIME / 25°C:	1 – 1¼ Hours			
EXOTHERM: (500ml volume)	Maximum 60°C			
ADHESION:	To PVC, Aluminium, Lead, Copper: Very good			
	To Cleaned, Flame	ed Polyeth	ylene: Good	
FLASHPOINT:	> 200°C			
HEAT RESISTANCE:	Maximum 80°C			
HARDNESS: (Cured 24h / 25°C)	Shore D: 80 – 85			
DIELECTRIC STRENGTH: (Method 210C)	21 kV/mm			
VOLUME RESISTIVITY:	10 x 10 ¹² Ohm/cm			
RESISTANCE:	To Water, Oil, dilut	ed Acids,	Alkaline:	Very good
	Solvents: Aromation	c / Aliphat	ic Hydrocarbons:	Good
	Esters, Ketons, Ch (Individual tests are	lorinated Hydrocarbons:		Not resistant
	(Individual lesis all		unucuj	2/

2/....

Page 2 FR/453

HYDROLYTIC STABILITY:	Excellent		
WATER ABSORPTION:	(After 24 hour immersion in distilled water): 0.3 %		
STORAGE STABILITY:	12 Months stored under dry and cool conditions in sealed packaging		
TOXICITY:	Very low toxicity at ambient temperatures. However, gloves must be worn and adequate ventilation must be ensured during application.		
NOTICE	The technical specification and/or our technical advice whether verbal, in writing or by trials is given in good faith and based on our test results obtained but without warranty. It does not release the user from the obligation to test the products supplied by us or any third party as to the suitability for the intended application.		
	The application, use and processing of the products are beyond our control and Elite Chemical Industries legal obligation in respect of any sale of its products shall be determined by the terms of its conditions of sale.		